

Optical Limiting of CdSe Based Multiphase Polymer Nanocomposite Films

Jayesh Koher*

Department of Mathematical and Physical Sciences, Miami University Regionals, Middletown, USA

Abstract

Optical limiting is a nonlinear optical process where the transmission of light decreases with increasing light intensity, protecting sensitive optical devices and human eyes from damage by intense light sources such as lasers. Materials exhibiting optical limiting are of significant interest for applications in optical limiters and sensors. One promising class of materials for this purpose is semiconductor nanocrystals embedded in polymer matrices, particularly Cadmium Selenide (CdSe)-based multiphase polymer nanocomposite films. CdSe nanocrystals are semiconductor quantum dots that have attracted extensive research due to their unique optical properties, including size-tunable bandgaps, high photoluminescence quantum yields, and nonlinear optical responses. These properties arise from the quantum confinement effect, where the electronic and optical properties of the nanocrystals are controlled by their size and shape. CdSe nanocrystals can be synthesized using various methods, such as colloidal synthesis, which allows for precise control over their size and surface chemistry.

Keywords: Optical • Process • Polymer • Nanocomposite • Quantum • Nanocrystals

Introduction

Incorporating CdSe nanocrystals into polymer matrices results in nanocomposite materials that combine the advantageous properties of both components. The polymer matrix provides mechanical flexibility, ease of processing, and the ability to form thin films, while the CdSe nanocrystals contribute to the optical properties. The interaction between the nanocrystals and the polymer matrix can lead to enhanced optical limiting behaviour due to mechanisms such as nonlinear absorption, scattering, and multiphoton absorption. The fabrication of CdSe-based multiphase polymer nanocomposite films typically involves the dispersion of CdSe nanocrystals within a polymer matrix. This process can be achieved through solution blending, in situ polymerization, or melt processing. Solution blending is the most common approach, where CdSe nanocrystals are dispersed in a polymer solution, followed by film casting and solvent evaporation. The choice of polymer, solvent, and processing conditions significantly affects the dispersion and distribution of the nanocrystals within the polymer matrix [1-3].

In solution blending, the CdSe nanocrystals are first dispersed in a suitable solvent. Common solvents include chloroform, toluene, and Tetrahydrofuran (THF). The polymer, such as Polymethyl Methacrylate (PMMA), Polystyrene (PS), or Polyvinyl Alcohol (PVA), is then dissolved in the same or a compatible solvent. The nanocrystal dispersion is mixed with the polymer solution, and the mixture is cast into a film using techniques like spin coating or drop casting. The solvent is then evaporated, leaving behind a nanocomposite film. In situ polymerization involves the dispersion of CdSe nanocrystals in monomer solutions, followed by polymerization to form the polymer matrix. This method ensures better dispersion and interaction between the nanocrystals and the polymer. For example, CdSe nanocrystals can be dispersed in a Methyl Methacrylate (MMA) monomer solution, followed by polymerization to form a PMMA matrix. Melt processing is less common but can be used for thermoplastic polymers. CdSe nanocrystals are mixed with

**Address for Correspondence:* Jayesh Koher, Department of Mathematical and Physical Sciences, Miami University Regionals, Middletown, USA; E-mail: koherjayesh54@gmail.com

Copyright: © 2024 Koher J. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Received: 01 May, 2024, Manuscript No. jlop-24-138248; **Editor Assigned:** 03 May, 2024, PreQC No. P-138248; **Reviewed:** 15 May, 2024, QC No. Q-138248; **Revised:** 22 May, 2024, Manuscript No. R-138248; **Published:** 29 May, 2024, DOI: 10.37421/2469-410X.2024.11.140

the polymer in the molten state, followed by extrusion or molding to form films. This method requires careful control of temperature and shear conditions to prevent aggregation of the nanocrystals. The optical properties of CdSe-based multiphase polymer nanocomposite films are characterized using various techniques. UV-Vis absorption spectroscopy, photoluminescence spectroscopy, and nonlinear optical measurements are commonly employed to study the optical limiting behaviour of these materials [4].

Literature Review

UV-Vis absorption spectroscopy provides information about the absorption characteristics of the nanocomposite films. The absorption spectrum of CdSe nanocrystals shows a size-dependent blue shift due to the quantum confinement effect. The position and intensity of the absorption peaks can be used to estimate the size and concentration of the nanocrystals in the polymer matrix. Photoluminescence (PL) spectroscopy measures the emission properties of the nanocomposite films. The PL spectrum of CdSe nanocrystals typically shows a sharp emission peak corresponding to the bandgap energy. The PL intensity and peak position can provide information about the quality and dispersion of the nanocrystals within the polymer matrix.

Nonlinear optical measurements, such as z-scan and pump-probe techniques, are used to study the optical limiting behaviour of the nanocomposite films. These techniques measure the intensity-dependent transmission and absorption of the films, providing insights into the mechanisms responsible for optical limiting. The optical limiting behaviour of CdSe-based multiphase polymer nanocomposite films can arise from several mechanisms, including nonlinear absorption, scattering, and multiphoton absorption. Nonlinear absorption, such as Two-Photon Absorption (TPA) and Three-Photon Absorption (3PA), occurs when the material absorbs multiple photons simultaneously. CdSe nanocrystals exhibit strong nonlinear absorption due to their high density of states and quantum confinement effects. In the case of TPA, the material absorbs two photons of lower energy, resulting in a transition to a higher energy state. This process leads to a reduction in the transmitted intensity at high light intensities, contributing to optical limiting [5].

Discussion

Scattering can also contribute to optical limiting. When CdSe nanocrystals are dispersed in a polymer matrix, they can form aggregates or clusters that scatter light. This scattering increases with light intensity, leading to a decrease in the transmitted light. The size and distribution of

the nanocrystals within the polymer matrix affect the scattering behaviour. Multiphoton absorption, involving the simultaneous absorption of more than two photons, can also occur in CdSe nanocrystals. This process is more pronounced at higher light intensities and can lead to efficient optical limiting. The large nonlinear absorption coefficients of CdSe nanocrystals make them suitable for multiphoton absorption-based optical limiting. Several factors influence the optical limiting performance of CdSe-based multiphase polymer nanocomposite films, including the size and concentration of CdSe nanocrystals, the choice of polymer matrix, and the film thickness. The size of CdSe nanocrystals significantly affects their optical properties. Smaller nanocrystals exhibit stronger quantum confinement effects, leading to larger nonlinear absorption coefficients. However, very small nanocrystals can be prone to aggregation, which can affect the dispersion in the polymer matrix and the overall optical limiting performance.

The concentration of CdSe nanocrystals in the polymer matrix also plays a crucial role. Higher concentrations can enhance the nonlinear optical response but may lead to aggregation and scattering losses. An optimal concentration needs to be achieved to balance these effects and maximize optical limiting performance. The choice of polymer matrix affects the dispersion, interaction, and stability of CdSe nanocrystals. Polymers with good compatibility and interaction with the nanocrystals, such as PMMA, can lead to better dispersion and enhanced optical limiting. The refractive index, mechanical properties, and process ability of the polymer matrix also influence the overall performance of the nanocomposite films. The thickness of the nanocomposite film determines the optical path length and the interaction of light with the material. Thicker films can provide better optical limiting performance but may suffer from increased scattering and absorption losses. An optimal film thickness needs to be determined based on the specific application requirements. CdSe-based multiphase polymer nanocomposite films have potential applications in various fields, including laser protection, optical sensors, and photonic devices [6].

Conclusion

One of the primary applications of optical limiting materials is in laser protection. These materials can protect sensitive optical components and human eyes from damage by intense laser beams. CdSe-based nanocomposite films can be used as optical limiters in protective eyewear, optical filters, and sensor protection. Optical sensors can benefit from the nonlinear optical properties of CdSe-based nanocomposite films. These materials can be used to develop sensors that detect high-intensity light or measure optical power. The tunable optical properties of CdSe nanocrystals enable the design of sensors with specific wavelength responses. CdSe-based nanocomposite films can be integrated into photonic devices, such as optical switches and modulators, due to their nonlinear optical response. The ability to control light transmission and absorption with intensity makes these materials suitable for advanced photonic applications. Despite the promising potential of CdSe-based multiphase polymer nanocomposite films for optical limiting applications, several challenges need to be addressed.

Acknowledgement

None.

Conflict of Interest

None.

References

1. Bhowmick, Mithun, Bruno Ullrich, Madeline Murchland and Xuan Zhou, et al. "Substrate and excitation intensity dependence of saturable absorption in perovskite quantum dot films." *Nanomaterials* 13 (2023): 871.
2. Bhowmick, Mithun, James Christensen, Richard Adjorlolo and Bruno Ullrich. "Photoluminescence from two-phase nanocomposites embedded in polymers." *Micromachines* 15 (2024): 111.
3. Seitz, Michael, Patricia Gant, Andres Castellanos-Gomez and Ferry Prins. "Long-term stabilization of two-dimensional perovskites by encapsulation with hexagonal boron nitride." *Nanomaterials* 9 (2019): 1120.
4. Hou, Xiaoqi, Jun Kang, Haiyan Qin and Xuewen Chen, et al. "Engineering auger recombination in colloidal quantum dots via dielectric screening." *Nat Commun* 10 (2019): 1750.
5. Kagan, C. R., C. B. Murray, M. Nirmal and M. G. Bawendi. "Electronic energy transfer in CdSe quantum dot solids." *Phys Rev Lett* 76 (1996): 1517.
6. Elumalai, Dhanumalayan, Beatriz Rodríguez, Ganna Kovtun and Pedro Hidalgo, et al. "Nanostructural characterization of luminescent polyvinyl alcohol/graphene quantum dots nanocomposite films." *Nanomaterials* 14 (2023): 5.

How to cite this article: Koher, Jayesh. "Optical Limiting of CdSe Based Multiphase Polymer Nanocomposite Films." *J Laser Opt Photonics* 11 (2024): 140.